



Kronoflooring GmbH Mühlbacher Straße 1 01561 Lampertswalde/Germany Ph. +49 3522 33 30 • Fax: +49 3522 33 399 info@kronoflooring.com

Technical Datasheet Herringbone

Direct Pressure Laminate, Level of use according to EN 13329: class 23/32 - AC5







Heavy domestic use

Commercial general use

The guarantee applies to the living area according to warranty regulations*

	NS	

dimension	thickness (d)	8 ± 0,50 mm · dmax - dmin ≤ 0,50 mm			
	length	630 ± 0,50 mm			
	width (b)	126 ± 0,10 mm · bmax - bmin ≤ 0,20 mm			
profile	long side	angle angle	short side	fold down	
groove	long side	real groove	short side	real groove	

EN 13329	≤ 0,20 mm
EN 13329	≤ 0,30 mm
EN 13329	concave: ≤ 0,15% · convex: ≤ 0,20%
EN 13329	concave: ≤ 0,50% · convex: ≤ 1,00%
EN 13329	average: ≤ 0,15 mm · max: ≤ 0,20 mm
EN 13329	average: ≤ 0,10 mm · max: ≤ 0,15 mm
	± 2 mm
	EN 13329 EN 13329 EN 13329 EN 13329

misalignment			± 2 mm		
TEST	TEST				
abrasion resistance		EN 13329	AC5 (≥ 6000 rpm)		
impact resistance		EN 13329	small ball ≥ 70 mm · big ball ≥ 1000 mm		
stain resistance	group 1 & 2	EN 13329	grade 5		
	group 3	EN 13329	≥ grade 4		
castor chair test		EN 13329	no change in appearance or damage, as defined per EN 425		
effect of a furniture leg		EN 13329	no damage shall be visible, when testet with foot type 0		
static indentation		EN 13329	≤ 0,05 mm		
light fastness		EN 13329	grey scale ≥ 4 at blue wool grade 6		
dimensional variations after changes in relative humidity		EN 13329	lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm		
locking strength		EN 13329	length ≥ 1 kN/m · width ≥ 2 kN/m		
surface soundness		EN 13329	≥ 1,25 N/mm²		
ENVIRONMENT					

E	٧V	IK	Or	NIN	Er	V

emission of formaldehyde EN 16516 class E1

PHYSICAL BEHAVIOR

fire behavior	EN 13501-1	Cfl s1			
slide resistance	EN 13893	technical class DS			
thermal resistance	EN 12667	0,073 (m ² K)/W ± 15%			
thermal conductivity	EN 12664	0,110 W/(m*K) ± 15%			

^{*}Detailed warranty conditions are available at www.krono-original.com